



## DATA SHEET

### Filter media

Cellulose Flame Retardant

### Cellulose Flame Retardant

<b>Appearance</b>	Yellow/Brown
<b>Use</b>	Pleatable filter media
<b>Composition</b>	Cellulose fibre filter media
<b>Area weight</b>	128 g/m <sup>2</sup>
<b>Air Permeability</b>	520 m <sup>3</sup> /m <sup>2</sup> /h at 200 Pa
<b>Surface electrical resistance</b> (DIN 54345)	-
<b>IFA/BIA certificate</b> (DIN EN 60335-2-69:2015)	L
<b>Temperature (dry heat)</b>	
Continuous	50 °C
<b>Chemical resistance</b>	
Hydrolysis	N/A
Acids	Poor
Alkalis	Fair
Oxidising agents	Poor
Organic solvents	Fair
<b>Dust release</b>	Very Good
<b>Supports combustion</b>	Fire class F1 according to DIN 53438